



## TA35 FVNG RA

## TABELLE WÄRMEDURCHGANGSKOEFFIZIENT

GENERAL BASICS FOR CALCULATION
Calculation Uw Element Size 1.135 mm x 2.325 mm
Basics for Calculation:
DIN EN ISO 10077-1, DIN EN ISO 10077-2, DIN EN 13947 DIN 4108, DIN EN 673
Basis of calculation is standard frame widths.
If the proportion of the glass surface increases in relation to the frame surface, the Uw-value improves.
The assignment of the types of wood to the thermal conductivities (TC) is made according to DIN EN ISO 10077-2 [2012-06].
Formula for Calculation:
$\frac{\Sigma (A_g \times U_g) + \Sigma (A_f \times U_f) + \Sigma (l_g \times Y_g) + \Sigma (A_p \times U_p)}{\Sigma (A_g + A_f + A_p)}$

DEFINITIONS VARIABLES	
Glass Surface	Ag
Frame Surface	Af
Panel Surface	Ap
Length Edge Seal	Lg
Heat Transfer Coefficient of Glass	Ug
Heat Transfer Coefficient of Frame	Uf
Heat Transfer Coefficient of Panel	Up
Heat Transfer Coefficient of Edge Seal	ψg

BASICS FOR CALCULATION U-VALUES	
Plastic Edge Seal Double Insulated Glazing	0,040 W/mK
Plastic Edge Seal Triple Insulated Glazing	0,035 W/mK
Heat Insulation Panel	0,035 W/mK

TYPE OF WOOD CLASS	PROFILING	UF W/(m²K)	UG 1,1/ DOUBLE, ISO	UG 1,0/ DOUBLE, ISO	UG 0,7/ TRIPLE, ISO	UG 0,6/ TRIPLE, ISO	UG 0,5/ TRIPLE, ISO
<b>1 - TC=0,110 W/(m²K)</b>	68	1,15	1,21	1,13	0,90	0,82	0,75
Fir, Spruce	78	1,08	1,19	1,11	0,88	0,80	0,73
Silver Fir	88	1,03	1,17	1,10	0,87	0,79	0,72
<b>2 - TC=0,130 W/(m²K)</b>	68	1,27	1,24	1,16	0,93	0,85	0,78
Pine, Douglas Fir	78	1,19	1,22	1,14	0,91	0,83	0,76
Larch, Hemlock	88	1,14	1,20	1,13	0,89	0,82	0,75
<b>3 - TC=0,160 W/(m²K)</b>	68	1,43	1,28	1,20	0,97	0,90	0,82
Meranti, Teak	78	1,35	1,26	1,18	0,95	0,87	0,80
Eucalyptus	88	1,29	1,24	1,17	0,93	0,86	0,78
<b>4 - TC=0,180 W/(m²K)</b>	68	1,53	1,30	1,23	1,00	0,92	0,85
Oak	78	1,45	1,28	1,21	0,97	0,90	0,83
White Oak	88	1,39	1,27	1,19	0,96	0,88	0,81

The Uw values change depending on the element's structure and size. Frame widths and choice of edge seal equally influence these values. We gladly calculate concrete Uw values of the window elements of your project. The current batimet conditions at [www.batimet.com](http://www.batimet.com) are valid. Technical changes are reserved. State of 12/03/2016. You can find current details via: